

PRODUCT DATA SHEET

Sikaflex® Connection

1-COMPONENT, JOINT SEALANT ADHESIVE FOR INDOOR AND OUTDOOR APPLICATIONS

DESCRIPTION

Sikaflex® Connection is a 1-component, moisture-curing, high-modulus elastic joint sealant for indoor and outdoor application.

USES

Sikaflex® Connection is designed for the movement joint sealing and bonding in concretes. (eg. joint for doors and windows, pipes and ventilation construction, metals and woods, joint between stairs and walls.)

CHARACTERISTICS / ADVANTAGES

- Very good workability
- Solvent-free
- Very good adhesion to most construction materials
- Very good workability

APPROVALS / STANDARDS

- JCT 881 20HM

PRODUCT INFORMATION

Chemical base	i-Cure® Technology polyurethane
Packaging	600 ml foil pack, 20 foil packs per box
Colour	White, Grey, Black
Shelf life	Sikaflex® Connection has a shelf life of 12 months from the date of production, if it is stored in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	Sikaflex® Connection shall be stored in dry conditions, where it is protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Density	~ 1.25 kg/l (ISO 1183-1)

TECHNICAL INFORMATION

Shore A Hardness	~ 40 (after 28 days)	(ISO 868)
Elongation at Break	~ 250 %	(ISO 37)
Elastic Recovery	~ 70 %	(ISO 7389)
Tear Propagation Resistance	~ 6.5 N/mm	(ISO 34)
Secant Tensile Modulus	≤ 0.40 N/mm ² 100% elongation (23 °C) ≤ 0.60 N/mm ² 100% elongation (-20 °C)	(ISO 8339)

Service Temperature

-40 °C-- +90 °C

Joint Design

The joint width must be designed to suit the joint movement required and the movement capability of the sealant. The joint width shall be ≥ 10 mm and ≤ 35 mm. A width to depth ratio of 2:1 must be maintained.

All joints must be correctly designed and dimensioned in accordance with the relevant standards, before their construction. The basis for calculation of the necessary joint widths are the type of structure and its dimensions, the technical values of the adjacent building materials and the joint sealing material, as well as the specific exposure of the building and the joints.

For larger joints please contact Sika Technical Service.

APPLICATION INFORMATION

Consumption

Joint width [mm]	10mm	15mm	20mm	25mm	30mm
Joint depth [mm]	8mm	8mm	10mm	12mm	15mm
Joint length [m]	~7.5m	~4.5m	~2.5m	~1.6m	~1.3m

Backing Material

Use closed cell, polyethylene foam backing rods.

Sag Flow

~ 0 mm (20 mm profile, 50 °C)

(ISO 7390)

Ambient Air Temperature

+5 °C-- +35 °C

Substrate Temperature

+5 °C-- +35 °C, 3 °C above dew point temperature

Curing Rate

~ 4 mm/24 hours(23 °C / 50% r.h.)

(CQP 049-2)

Skin time

~ 50 minutes(23 °C / 50% r.h.)

(CQP 019-1)

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Sikaflex® Connection adheres without primers and/or activators.

However, for optimum adhesion and critical, high performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed:

Non-porous substrates

Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated using Sika® Aktivator 205, wiped on with a clean towel. Before sealing, allow a flash-off time of > 15 minutes (< 6 hours). Other metals, such as copper, brass and titanium-zinc,

also have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further flash-off time of > 30 minutes (< 8 hours) before sealing the joints. PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a flash-off time of > 30 minutes (< 8 hours).

Porous substrates

Concrete, aerated concrete and cement based renders, mortars and bricks shall be primed using Sika® Primer-3 N applied with a brush. Before sealing, allow a flash-off time of > 30 minutes (< 8 hours).

For more detailed advice and instructions please contact Sika Technical Services.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly.

APPLICATION METHOD / TOOLS

Sikaflex® Connection is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a foil pack or cartridge into the sealant gun and extrude Sikaflex® Connection into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikaflex® connection must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time. Use a compatible tooling agent (e.g. Sika® Tooling Agent N) to smooth the joint surfaces. Do not use tooling products containing solvents.

CLEANING OF TOOLS

Clean all tools and application equipment immediately after use with Sika® Remover-208 and/or Sika® Cleaning Wipes-100. Once cured, residual material can only be removed mechanically.

FURTHER DOCUMENTS

- Safety Data Sheet (SDS)
- Pre-treatment Chart Sealing & Bonding
- Method Statement Joint Sealing
- Method Statement Joint Maintenance, Cleaning and Renovation

LIMITATIONS

- Sikaflex® Connection can be overpainted with most conventional facade coating paint systems. However, paints must first be tested to ensure compatibility by carrying out preliminary trials (e.g. according to ISO technical paper: Paintability and Paint Compatibility of Sealants). The best over-painting results are obtained when the sealant is allowed to fully cure first. Note: non-flexible paint systems may impair the elasticity of the sealant and lead to cracking of the paint film.
- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation (especially with the colour shade white). However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Before using Sikaflex® Connection on natural stone, please refer to Sika Technical Service for advice.
- Do not use Sikaflex® Connection on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use Sikaflex® Connection to seal joints in and around swimming pools.
- Do not use Sikaflex® Connection joints under water pressure or for permanent water immersion.
- Do not expose uncured Sikaflex® Connection to alcohol containing products as this may interfere with the curing reaction.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA (CHINA) LTD.

28# Jing Dong Road
Suzhou Industrial Park
Jiangsu 215121, P.R. China

Tel: 0512-62732888

Chn.sika.com

Target Market: Sealing Bonding